

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵: D01F 9/12, C01B 31/02	A1	(11) International Publication Number: WO 94/15004 (43) International Publication Date: 7 July 1994 (07.07.94)
(21) International Application Number: PCT/US93/11715 (22) International Filing Date: 3 December 1993 (03.12.93) (30) Priority Data: 993,540 21 December 1992 (21.12.92) US (71) Applicant: OLIN CORPORATION [US/US]; 350 Knotter Drive, P.O. Box 586, Cheshire, CT 06410-0586 (US). (72) Inventors: ASHOK, Sankaranarayanan; 44 Old Fairwood Road, Bethany, CT 06525 (US). CHESKIS, Harvey, Perry; 4 Country Way, North Haven, CT 06473 (US). PASQUALONI, Anthony, Mark; 219 Fairview Avenue, Hamden, CT 06514 (US). OSMENT, Donald, Richard; 2772 Madison Court, East Petersburg, PA 17356 (US). (74) Agents: ROSENBLATT, Gregory, S. et al.; Wiggin & Dana, One Century Tower, New Haven, CT 06508-1832 (US).		(81) Designated States: AU, BB, BG, BR, BY, CA, CZ, FI, HU, JP, KP, KR, KZ, LK, MG, MN, MW, NO, NZ, PL, RO, RU, SD, SK, UA, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: RECOVERY OF CARBON FIBERS FROM EPOXY WASTE (57) Abstract <p>Burning off the epoxy resin from graphite-epoxy composite waste to recover carbon fibers provides a method to recover the fibers substantially intact and without the use of chemical solvents. The waste is heated to a temperature in the range of about 375 °C to about 600 °C for a time sufficient to decompose the epoxy through oxidation.</p> <div data-bbox="688 1121 1429 1717"><p>100X 100 μm</p></div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

RECOVERY OF CARBON FIBERS
FROM EPOXY WASTE

This invention relates generally to methods for recovering carbon fibers. More particularly, the invention relates to methods for recovering carbon fibers from graphite-epoxy machining waste.

5 Graphite-epoxy composite materials containing carbon fibers are used in military ordnance because of their high strength-to-weight and high modulus to weight ratios. For example, such composites are used in discarding sabots for kinetic energy
10 projectiles such as 120mm KE anti-tank rounds. The large volume of such ordnance produced results in a significant quantity of machining scrap. Some estimates are that there is about a billion dollars worth of carbon fibers in such machining scrap.

15 Until the present invention, there has been no known method for recovering the carbon fibers from such waste. The problem has been to separate the fibers from the epoxy resins in which they are contained.

20 Attempts to date have apparently been unsuccessful because the fibricity of the fibers has been destroyed in the recovery process. Apparently attempts to date have centered around chemical solvents and have involved trying to selectively
25 dissolve the epoxy without damaging the carbon fibers, but such attempts have been unsuccessful.

 A new technical approach is needed which can separate the carbon fibers from the surrounding epoxy without significantly weakening the carbon
30 fibers.

 These problems are solved in the process of the present invention described and claimed below in which the graphite-epoxy composite material is heated to a critical temperature range and held

-2-

there a certain time, so as to decompose and oxidize the epoxy resin without degrading the carbon fibers.

The invention stems from the understanding that the carbon fibers burn at a higher temperature than the epoxy resin and that the carbon fibers are not significantly degraded at the burning temperature of the epoxy resin. The invention thus solves a significant environmental problem in an extremely simple and effective way to give the potential for recovering over a billion dollars worth of valuable and expensive carbon fibers.

Composites containing the carbon fibers have been in use for several decades without this unexpectedly effective simple solution having been discovered, so this solution has not been obvious to those of ordinary skill in the art. It simply has not previously been thought that one could save the carbon fibers by burning them.

The invention will be better understood by referring to the accompanying drawings, in which:

Figure 1 is a scanning electron microscope (SEM) photograph of the graphite-epoxy resin composite after thermal treatment by the method of the invention.

Figure 2 is a SEM photograph of the resin of Figure 1 before thermal treatment.

Figure 3 is a line graph showing the experimentally calculated percentage weight loss of graphite-epoxy resin held at various temperatures for one hour.

Figure 4 is a line graph showing the percentage weight loss of graphite-epoxy resin when held for varying times at 400°C.

Carbon fiber/epoxy composite materials are being extensively used in structures where light weight, high strength, and high stiffness are

-3-

desired or required. In most applications, the composite material is fabricated to a "near-net" condition and various degrees of machining take place after the curing operation to complete the article. In large volumes, the composite machining waste constitutes a considerable value in unclaimed carbon fiber. Samples of machining waste were analyzed, and indeed found to contain a high volume fraction (>60%) of the expensive carbon fibers. Hence it is worthwhile to recover these carbon fibers, and investigate potential "recycle" markets.

It has been found that if the composite waste is heated in air at temperatures in the range of 375° - 600°C for varying periods of time, that enough energy can be obtained to effect epoxy resin decomposition (oxidation) without degrading the carbon fibers. (See Figures 1 and 2). This thermal treatment breaks down the epoxy resin into the volatile compounds, which evaporate and leave clean carbon fibers behind. It is believed that aeration during the treatment will enhance the loss of epoxy, while also promoting the formation of environmentally sound compounds, i.e. CO₂ and H₂O. Thermally treated waste was observed by Scanning Electron Microscopy (SEM) analysis, and showed that the carbon fibers had a surface quality equivalent to the untreated carbon fiber. (See Figure 2).

The temperature used for treating the waste is critical. If the heat treatment is carried out at lower temperatures, significant portions of the epoxy remain attached to the fibers, even when held for extended time periods. This was experimentally observed at the 300°C temperature level. Above 600°C, the fiber oxidation reaction begins to accelerate, as monitored by excessive fiber weight loss.

-4-

Time at temperature is also important for complete removal of the epoxy. At an optimum temperature of 400°C, a 30 minute soak is insufficient to remove all resin, whereas a two hour
5 period appears to eliminate most of the epoxy (Figure 2). These factors will also depend upon other variables such as volume of waste material being treated, pan type and size, atmosphere being used, and air flow rates.

10 The preferred temperature range for burning off the epoxy resin used in the composites for 120mm KE ammunition sabots is 400-500°C. The objective is to burn off the epoxy with minimum damage to the carbon fibers. Likewise the time at which the materials
15 are held at the burning temperature should be enough to be sure essentially all the epoxy is burnt off and no longer, as any longer merely wastes energy. The preferred time is about 4 hours for the machining scrap from 120mm KE ammunition sabots.

20 The preferred process would use an afterburner to oxidize any volatilized epoxy resin compounds, so that only fully oxidized compounds are released to the atmosphere.

EXAMPLES

25 Example 1:

Five samples of graphite-epoxy resin composite waste from machining of 120mm KE ammunition sabots (plastic sheaths used in anti-tank ammunition) were heated to and held for one hour at, respectively,
30 300°C, 400°C, 500°C, 600°C, and 700°C. The composite samples were known to contain about 69% (by weight) carbon fibers and about 31% by weight epoxy resin. The weight loss resulting from this heating is shown in Figure 3. The data indicates
35 that all the epoxy resin is burnt off in one hour at about 450°C.

-5-

Example 2:

Four samples identical to those in Example 1 were heated to 400°C and held there for times, respectively, of 1, 1, 2, and 4 hours. The results are shown in Figure 4. It is seen that after about 4 hours, no further significant change in weight is noted and the weight loss is equal to the calculated weight % of epoxy resin (31%). This indicates that at 4 hours, substantially all the resin is gone and substantially all the carbon fibers remain.

While the invention has been described above and below with references to preferred embodiments and specific examples, it is apparent that many changes, modifications and variations in the materials, arrangements of parts and steps can be made without departing from the inventive concept disclosed herein. For example, in employing the heating method of the present invention to fiber-epoxy resin systems with different particle sizes and different specific resins, the preferred temperature may vary. Simple weight loss experiments can be run to analyze the amount of material decomposed and volatilized during the burning process. The weight loss data from such experiments can be compared with the known percentage by weight of carbon fibers in the composite to determine the amount of epoxy left, if any. The burning time and temperature can then be adjusted to an optimum amount to obtain nearly complete burning of the epoxy. Scanning electron microscope analysis of the residual material can be employed to confirm that carbon fibers are still intact after the burning process. Similarly, the medium in which the burning occurs can be varied to determine if a particular medium produces better recovery. Since the really significant discovery in

-6-

the present invention is that the fibers can be recovered from the composite by burning the composite at a temperature within a certain range.

- 5 Accordingly, the spirit and broad scope of the appended claims is intended to embrace all such changes, modifications and variations that may occur to one of skill in the art upon a reading of the disclosure.

-7-

IN THE CLAIMS:

1. A method of recovering carbon fibers from graphite-epoxy composite materials, characterized by the steps of:

- 5 a.) heating the composite materials to a temperature within the range of from about 375° to about 600° Centigrade, and
- b.) maintaining the materials within the range for a time period sufficient to remove the desired
- 10 percentage of epoxy resin.

2. The method of claim 1, characterized in that the materials are maintained within the range for at least two hours.

3. The method of claim 2, characterized in

15 that the materials are maintained within the range for at least four hours.

4. The method of claim 2, characterized in that the materials are maintained within the range for no more than about eight hours.

20 5. The method of claim 1, characterized in that the materials are heated to a temperature within the range of from about 375°C to about 500°C.

6. The method of claim 1, characterized in that the materials are heated to a temperature

25 within the range of from about 400°C to about 500°C.

7. The method of claim 1, characterized in that the materials are in an air environment during the heating and maintaining steps.

-8-

8. The method of claim 1, characterized in
that the step of heating the vapors resulting from
the material heating and maintaining steps in an
oxygen-containing gas to a temperature sufficient to
5 fully oxidize the vapors is included.

1/2



100X

100 μm

FIG. 1



100X

100 μm

FIG. 2




FIG. 3




FIG. 4

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US93/11715**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(5) :D01F 9/12; C01B 31/02

US CL :423/447.1, 447.2, 461

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 423/447.1, 447.2, 461, 460, 445

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS (waste, scrap, epoxy, recover, recycle, salvage, graphite)

CAS ONLINE (waste, scrap, tire, rubber, epoxy, fiber recover, recycle, salvage)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	Lederer et al., "Recycling of Fibre-Reinforced Duroplastics,"	1, 5, 6
--	Radex-Rundschau, Vol. 3/4, November 1991, see pages	-----
Y	537-540.	2-4, 7-8
Y	Freeman, Standard Handbook of Hazardous Waste Treatment & Disposal, pages 8.91 -8.97, especially page 8.92, 8.96, Table 8.7.1, 1989.	7-8

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be part of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

03 FEBRUARY 1994

Date of mailing of the international search report

23 FEB 1994

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

STEVE KALINCHAK

Telephone No. (703) 308-0661